

NYLO FLEX®

XP3017 50cm wide

Nylo Flex has a mild sticky backing which makes intricate designs quick and simple to produce. It is suitable for application to 100% nylon products. Nylo Flex is easy to cut, weed and apply.

A4 samples are available free of charge upon request, for larger samples 1m rolls are available to purchase.

STEP BY STEP

STEP 1

Cut your design in mirror image
Film blade required.

STEP 2

Weed away any excess material.

STEP 3

Place transfer face down onto the garment with the transparent backing on top and press for 20 seconds at 150°C.

STEP 4

Remove the transparent backing cold, cover with silicone paper and re-press for a further 10 seconds.

DURABILITY

30°C

MICRONS

50-60

FINISH

Semi Matt

TACK

Medium

PEEL

Cold

PU OR PVC

PU

PRODUCT INFORMATION

SIZE: 50cm wide x 1m, 5m & 20m rolls

CUTTING FORCE: Film Blade from 30gf *

TRANSFER LAYERING: No

SUITABLE FOR

100% NYLON (uncoated garment only)

TRANSFER SETTINGS

TIME 20 seconds + 10 seconds

TEMP 150°C

PRESSURE Medium

PEEL Cold

ACCREDITATIONS



CLASS 1



CARE INFORMATION

WASH UP TO 30°C

DO NOT DRY CLEAN

DO NOT TUMBLE DRY

DO NOT IRON

STORAGE (Store vertically in a dry room between 15-30°C)

* All force testing has been undertaken using a NEW blade on a Roland GS24. The force will increase with the age of the blade, therefore always test prior to use.

PLEASE NOTE: The sellers and manufacturers maximum obligation shall be to replace any product that has been proven to be defective. Neither the seller nor the manufacturer of Nylo Flex shall be liable for any injury direct or consequential, arising out of the use of, or inability to use this range. Nylo Flex has been tested using uncoated Nylon, when applying to coated Nylon results may vary, testing prior to purchase is recommended.



Web: www.xpres.co.uk Support www.xprestechnical.co.uk

Oakridge Park, Trent Lane, Castle Donington, Derby DE74 2PY Phone: 01332 855 085 E-mail: sales@xpres.co.uk

* All force testing has been undertaken using a NEW film blade on a Roland GS24. The force will increase with the age of the blade, therefore always test prior to use.